




CUPA 14

*Non-carbonated **slate** formed by tectonic compression.
Dark grey slate with thin laminations and a **riven surface**.*





Quarry Las Fuentes. Benuza (León)
Spain.



Operating since 1985.



Main sizes: 8"x6" to 24"x12"
Thickness: 3/16" to 3/8"



Formats



Rectangular

Selections

EXCELLENCE

ARDOISIER

HEAVY

Technical specifications

ABSORPTION	CARBONATE NON CARBONATED	MOR CHARACTERISTIC	SO ₂ EXPOSURE TEST	THERMAL CYCLE TEST	FREEZE THAW TEST
< 0,4% Code : W1 (< 0,4%)	≤ 0,2% Fullfil (< 2%)	Longitudinal ≥ 37 MPA	S1	T1	Fullfil < 0,4%

International certifications



European Standard: EN 12326 | British Standard: BS 680 Part 2